

## Significant effect of concentration ratio in synthesizing titania nanoflowers (TNF) powder via facile hydrothermal method

Faiz Hafeez Azhar <sup>a</sup>, Zawati Harun <sup>a,\*</sup>, Muhamad Zaini Yunos <sup>a</sup>, Azlinorazia Ahmad <sup>a</sup>, Siti Hajar Mohd Akhair <sup>a</sup>, Raja Adibah Raja Ahmad <sup>a</sup>, Abdul Qaiyum Abd Rashid <sup>a</sup>, Rosniza Hussin <sup>b</sup>, Siti Aida Ibrahim <sup>b</sup>, Mohd Khairul Ahmad <sup>c</sup>

<sup>a</sup> *Integrated Material and Process, Advanced Manufacturing and Materials Centre (AMMC), Institute Integrated Engineering (IIE), Faculty of Mechanical and Manufacturing Engineering, Universiti Tun Hussein Onn Malaysia, 86400, Parit Raja, Batu Pahat, Johor, Malaysia.*

<sup>b</sup> *Faculty of Mechanical and Manufacturing Engineering, Universiti Tun Hussein Onn Malaysia, 86400, Parit Raja, Batu Pahat, Johor, Malaysia*

<sup>c</sup> *Microelectronic and Nanotechnology – Shamsudin Research Centre (MiNT-SRC), Institute Integrated Engineering (IIE), Universiti Tun Hussein Onn Malaysia, 86400, Parit Raja, Batu Pahat, Johor, Malaysia*

\* Corresponding author: [zawati@uthm.edu.my](mailto:zawati@uthm.edu.my)

### Article history

Submitted 12 June 2018

Revised 27 June 2018

Accepted 16 July 2018

Published Online 3 September 2018

### Abstract

The significant effect of titanium butoxide and hydrochloric acid (TBut/HCl) concentration ratio in synthesizing titania nanoflowers (TNF) towards powder morphologies, crystallographic phases, surface area and band gap were investigated. Various synthesized titania nanostructure were prepared via facile hydrothermal method using titanium butoxide and hydrochloric acid as a mixing composition. The morphologies of synthesizing titania powder were analyzed by using FE-SEM to observe the shape and geometry of the synthesized powder. XRD was used to determine the crystallographic phases of synthesized powder at  $2\theta$  angles of  $25^\circ$  to  $75^\circ$ . Each sample was then investigated under BET analyzer to observe the particle surface area and UV-Vis analyzer to determine the band gap. The results demonstrated that the concentration of TBut/HCl ratio gave a very significant effect in transforming the mixing solution into geometrical shape of microspheres, nanoflowers and nanorods of titania as increasing the ratio. At TN0.5, the synthesized powder was clearly showing a circle geometrical shape of particles. The shape was suddenly changed into a round nanoflowers form consist of tiny nanorods at TN1. At TN1.5, the powder morphology shows the nanoflowers started to form in an irregular pattern. As the concentration ratio increased, the nanoflowers form disappeared and nanorods begin to clump. In addition, all synthesized powder was in rutile phases guided by XRD peaks and the band gap value reported from previous works. The particle surface area was also different for each sample since the geometrical shape of powder was changed by increasing the concentration (TBut/HCl) ratio. Thus, concentration ratio of the mixing composition plays a major role in transforming the overall morphologies and structures of hydrothermal synthesis titania particles.

**Keywords:** Titania nanoflower (TNF), titanium dioxide, nanostructure, titanium butoxide, hydrothermal method

© 2018 Penerbit UTM Press. All rights reserved

### INTRODUCTION

Nanoparticles Titanium dioxide ( $\text{TiO}_2$ ) is well known inorganic material which is commonly used for oxide semiconductor materials due to their unique properties of strong oxidizing power, non-toxic in nature, biological and structure stability, easy handling and low cost material (Byranvand *et al.*, 2013; Karkare, 2014; Di Paola *et al.*, 2013). Until recently, the nanostructured of  $\text{TiO}_2$  such as nanorods, nanotubes and nanoflowers was widely investigated due to its excellent improvement in various applications such as photocatalytic, solar energy conversion, paint, cosmetics, textiles and photovoltaics (Ahmad & Murakami, 2012; McNulty, 2008; Theivasanthi & Alagar, 2013). Many method has been introduced and proposed to prepare and modify the nanostructure of  $\text{TiO}_2$  powder, such as solvothermal method (Yang & Gao, 2006), direct oxidation method (Sun *et al.*, 2013), chemical vapor deposition (Qu *et al.*, 2013), electrodeposition (Mali *et al.*, 2012), sonochemical method (Prabhu & Poulouse, 2012), microwave method

(Roy, 2013), and hydrothermal method (Sekino, 2010; Safarpour *et al.*, 2015; Xu *et al.*, 2012)

The hydrothermal method is known as the most cost effective methods to synthesize the  $\text{TiO}_2$  nanostructured powders. Generally, synthesis using hydrothermal can be described as a process of growing a single crystal from an aqueous solution in an autoclave at high temperature followed by applying pressure parameter (Abdullahi *et al.*, 2017; Byrappa & Yoshimura, 2008). By using this simple approach, the morphologies or the structure of the semiconductor materials can be controlled by several variables such as precursor (Seok *et al.*, 2010), pH (Houas *et al.*, 2001), acid concentration (Song *et al.*, 2016), hydrothermal time (Huang *et al.*, 2012), and concentration ratio of the synthesize solution (Karkare, 2014; Miao *et al.*, 2015). Unfortunately, this approach involved high chemical reaction which can easily disturb and influences the preparation and synthesis steps and sometimes affects the overall synthesis time.

Basically,  $\text{TiO}_2$  has three different crystalline phases which are rutile phase (tetragonal), anatase phase (tetragonal) and brookite phase

(orthorhombic) (Kaplan *et al.*, 2016; Paulauskas *et al.*, 2013; Xu *et al.*, 2015). As known, the rutile phase is the most stable phase at high temperature condition, while anatase and brookite are metastable phases that could be transformed into rutile phases with annealing or calcination at very high temperature (Ahmad & Murakami, 2012; Reyes-Coronado *et al.*, 2008; Wang *et al.*, 2014)

In this study, we investigated the effect of concentration (TBut/HCl) ratio in synthesizing titania nanoflowers (TNF) powder, with the intention to further enhance the unique and special properties of TNF by providing more effective and reactive surface area that can be suitable for many applications.

## EXPERIMENTAL

### Materials

All chemicals were purchased from BG Oil Chem SDN, BHD. Titanium butoxide (TBut, reagent grade, 97%, Sigma-Aldrich) and hydrochloric acid (HCl, AR, 37%, QReC), were used as only synthesized materials. Absolute ethanol (EtOH, HmbG® Chemicals) was used in cleaning and naturalized titania nanoflower (TNF). Iso-propanol (C<sub>3</sub>H<sub>8</sub>O, AR, QReC) was used as solvent for band gap characterization.

### Synthesis of titania nanoflowers (TNF) by using facile hydrothermal method

Titania Nanoflowers (TNF) were synthesized by using titanium butoxide (TBut) and concentrated Hydrochloric Acid (HCl) as the only raw materials. Both solutions were mixed together by applying different concentration (TBut/HCl) ratio as shown in Table 1. The total weight of synthesized nanoflowers powder from each sample were also being included as further reference.

**Table 1** Synthesizing Titania nanoflowers (TNF) parameter.


Samples	TBut (ml)	HCl (ml)	Concentration ratio	Mass (g)
TN2.5	20	8	2.5	3.6
TN2	20	10	2	3.3
TN1.5	20	13	1.5	3
TN1	20	20	1	3.8
TN0.5	10	20	0.5	1.8

In sequence, the stated volume of HCl was added onto 20 ml of TBut, the mixture is then transferred into a Teflon-lined autoclave which has the maximum capacity of 50 ml. Then, the hydrothermal treatment was conducted at a temperature of 150 °C for 24 hours in an oven. At the end of the hydrothermal process, the Teflon-lined autoclave was removed from the oven and allowed to cool down naturally at room temperature. After that, the white precipitate was collected and went through a cleaning process using distilled water and ethanol for several times to naturalize the pH value before centrifuging at 7500 rpm. The white samples were dried in an oven for 24 hours at 80 °C. After drying process, the samples were ground using agate mortar to get the desired size of a fine powder. The synthesis process was illustrated in Fig. 1.

### Characterization of titania nanoflowers (TNF)

The structure and morphologies of the synthesized titania nanoflowers (TNF) was characterized by Field-Emission Scanning Electron Microscopy (FE-SEM, JOEL, JSM-7600F, 10kV). The samples for testing were prepared by sealed on top of carbon tape and purged using nitrogen gas. The phases of crystallographic TNF were carried out by X-ray diffraction (XRD) patterns using D8 Advanced Bruker System which operated at 40 mA and 45 kV with a 2θ range of 25°-75°. For surface area analysis, Brunauer Emmett Teller (BET) model V-Sorp 4800P was used by weighing 1g of each sample and through the process of degassing. After the degassing process, the sample's weight was measured again to get the actual sample weight for the analysis. The weighted sample was then fed in to the BET machine for the conduct of the analysis under a continuous full

immersion in liquid nitrogen throughout the process. Band gap characterization was carried out using UV-Vis Spectrophotometer model 'GENESYS 10S'. 0.05g TNF powder was diluted in Iso-propanol (IPA) solvent and sonicated for 15 minutes before filling into quartz cuvette. The used wavelength range was 300 nm to 800 nm



**Fig. 1** Titania Nanoflowers (TNF) synthesized process

## RESULTS AND DISCUSSION

### Morphologies and structure analysis


Fig. 2 shows the FESEM image of different morphologies obtained by synthesizing titania nanoflower (TNF) using a different concentration ratio of TBut/HCl. The obtained structures are microspheres, nanorods, and nanoflowers. Fig. 1(a) shows the image of Titania microsphere with the lowest concentration (TBut/HCl) ratio of TN0.5 after hydrothermal treatment for 24 hours at a temperature of 150 °C. As observed, the surface of Titania microsphere at x50 000 magnification shows an attachment of tiny nanorods that has not been disassembled with the diameter particle size of 1.70 μm – 5.49 μm. At TN1 ratio, the TNF was disassembled and produced nanorods segment containing numerous flower-like structure formation with the diameter size ranging from 240 nm – 1,500 nm. Meanwhile, for Fig. 1(c), the micrograph for TN1.5 ratio shows that the structure of the nanoflowers started to split up whereby the segment of nanorod begins to separate and detach from the nanoflower. The distribution of the nanorods particles was nonhomogenous and irregular in shape, and the irregular pattern of the nanorods particles was continued to be formed until the highest concentration (TBut/HCl) ratio of TN2.5. Based on FESEM images, it clearly showed that, at high concentration of (TBut/HCl), varying the HCl volume content ratio does affect the formation of nanoparticles morphologies of titania particles. The results also has tallied with (Phan *et al.*, 2009) where they stated that the HCl itself act as an inhibitor or accelerator for further self-assembly, nucleation, and the crystal growth inside titania during hydrothermal treatment. The HCl solvent play significant role on the titania particle growth by promoting its growth on the TiO<sub>2</sub> microsphere to form titania nanoflowers and titania nanorods shapes (Shinde *et al.*, 2011). Therefore, by decreasing the HCl volume the structure of nanorods begin to change from microspheres to titania nanoflower (TNF) structures with reduced diameter ranging from 240nm – 1500nm.

### Phase characterization

Fig. 3 shows the XRD pattern of synthesized Titania Nanoflowers (TNF) using varying concentration (TBut/HCl) ratio results. All diffraction peaks are referred to titanium dioxide (TiO<sub>2</sub>) rutile phase (JCPDS card no. 00-021-1276). The rutile diffraction peaks were showed at 2θ = 27.5°, 36.1°, 41.2°, 54.3° and 56.6°. All these peaks can be attributed to (110), (101), (111), (211), (220) plane for rutile phases and was in-line with previous synthesis reports (Hamed *et al.*, 2016; Li *et al.*, 2013; Min *et al.*, 2010)

Through XRD observation and analysis, the obtained result of XRD pattern was confirmed  $\text{TiO}_2$  by matching the peaks and plane with JCPDS data. However, the intensity level of each sample were slightly different. As observed, the intensity for TN0.5 was quite low compared to other samples. Nonetheless, as the volume of HCl is increased at TN1, the XRD peak intensity of the sample also increased. This finding was also proved by FE-SEM results where the nanoflowers formation begins to form from microsphere structure. However, the intensity peaks were decreased as the concentration ratio achieved at TN2.5. The phenomena might have occurred due to the surface morphologies of the

titanium nanoflowers (TNF) particles that started to break and separated from the main structure of nanoflower with scattered distributed which affected the intensity of crystallization. These results was also tally with (Ahmad & Murakami, 2015; Khalid *et al.*, 2015) where the clear form of nanoflowers generated with a good crystal structure compared to other samples thus give highest intensity peak. In addition, these varying rutile peaks intensity might be also caused by the different volume of acid that interrupt the hydrolysis rate of Titanium butoxide (TBut) and eventually reacted to the growth of  $\text{TiO}_2$  (Hamed *et al.*, 2016)



**Fig. 2** FESEM images of different concentration (TBut/HCl) ratio (a) TN0.5, (b) TN1, (c) TN 1.5, (d) TN2, (e) TN2.5.


**Surface area and band gap analysis**

Fig.4(a) shows the BET plot of synthesized titania nanoflowers (TNF) at different concentration (TBut/HCl) ratio. The specific surface area of TN0.5, TN1, TN1.5, TN2 and TN2.5 are 21.09 m<sup>2</sup>/g, 21.10 m<sup>2</sup>/g, 27.25 m<sup>2</sup>/g, 28.64 m<sup>2</sup>/g and 35.39 m<sup>2</sup>/g respectively. From the results, the surface area for each sample were increased gradually as the HCl volume decreased. As comparison, the results for TN0.5 and TN1 produced less significant different eventhough the particle size from FESEM result shows very much different. Whereas, TN2.5 samples produced the largest surface area compared to other samples due to its irregular shape of particles as detached from the nanoflowers structure. As reported in other works (Ma et al., 2016; Wu et al., 2006) by providing more effective surface area ultimately will produced less specific surface energy that able to increase reaction mechanism. Similar result also was reported by (He et al., 2013) that revealed the agglomeration of the nanorods particles for TN1.5, TN2 and TN2.5 as proved in FESEM observation able to increase the total surface area of the particles and provide less specific surface. As being observed in the above section, the concentration (TBut/HCl) ratio was able to produce titania nanopowder with different surface area and morphologies of particles, thus definitely this will influences the total surface area that can be of benefit towards improving the particle reactivity in certain applications.


The band gap (E<sub>g</sub>) of a semiconductor material can be identified from the Tauc plot of (αhν)<sup>2</sup> against photon energy (hν). The band gap value energy can be determined by extrapolating the curve across the x-axis shown in Fig. 4(b). From the results in Table 2, TN0.5 indicates the lowest band gap value compared to other samples. Smaller values of band gap can be described that the sample can absorb more photon and generates additional photo-generated electron-hole pairs to enhance the photocatalytic activity (Song et al., 2014; Tang et al., 2013; Yin et al., 2013). TN2.5 shows the highest result value by 3.05 eV. However, the value of band gap was still in the range of rutile phases as reported by previous studied which is lower than 3.2 eV anatase phase (Ahmad et al., 2017; Pal et al., 2007; Reyes-Coronado et al., 2008). These varying band gap values indicate that titania is strongly influenced by its morphology (Dhandayuthapani et al., 2016).

**Table 2** BET surface area and band gap results.

Samples	BET surface area (m <sup>2</sup> /g)	Band gap (eV)
TN2.5	35.39	3.05
TN2	28.64	2.99
TN1.5	27.25	2.95
TN1	21.10	2.79
TN0.5	21.09	2.76



**Fig. 3** X-ray diffraction (XRD) patterns analysis for different concentration (TBut/HCl) ratio



**Fig. 4** (a) BET plot of synthesized titania nanoflower (TNF) for all concentration (TBut/HCl) ratio and (b) Tauc plot of (αhν)<sup>2</sup> againsts photon energy (hν).



## CONCLUSION

Titania nanoflowers (TNF) was synthesized using facile hydrothermal method by varying the volume of hydrochloric acid (HCl) to control (TBut/HCl) ratio concentration. The volume of hydrochloric acid was able to change the morphologies and the structure of the synthesized titania as observed under FE-SEM images. Clear formation of nanoflowers was noticed at ratio TN1. There were also different type of structure obtained which are microsphere and nanorods. The patterns of XRD for all samples were also slightly different in term of intensity indicates that the affected crystallinity after varying the (TBut/HCl) ratio concentration. BET surface area and band gap results analysis for each titania sample showed that each mixing concentration ratio controlled by HCl volume able to change all morphologies, XRD pattern, BET surface area and band gap value characteristics as well.

## ACKNOWLEDGEMENT

This work was financially supported by the Universiti Tun Hussein Onn Malaysia under the Fundamental Research Grant vot 1621 and Transmultidisciplinary Research Grants vot T001.

## REFERENCES

- Abdullahi, T., Harun, Z., & Othman, M. H. D. (2017). A review on sustainable synthesis of zeolite from kaolinite resources via hydrothermal process. *Advanced Powder Technology*, 28(8), 1827–1840.
- Ahmad, M. K., Abdul Aziz, A. F., Soon, C. F., Nafarizal, N., Noor Kamalia, A. H., Masaru, S., & Murakami, K. (2017). Rutile phased Titanium Dioxide (TiO<sub>2</sub>) Nanorod/Nanoflower based waste water treatment device. In R. Jabłoński & R. Szewczyk (Eds.), *Recent Global Research and Education: Technological Challenges: Advances in Intelligent Systems and Computing* (pp. 483–490). Springer, Cham.
- Ahmad, M. K., & Murakami, K. (2012). Low Temperature and Normal Pressure Growth of Rutile-phased TiO<sub>2</sub> Nanorods/Nanoflowers for DSC Application Prepared by Hydrothermal Method. *Journal of Advanced Research in Physics*, 3(2), 2011–2013.
- Ahmad, M. K., & Murakami, K. (2015). Rutile-phased TiO<sub>2</sub> nanorods/nanoflowers based Dye-sensitized solar cell. *Applied Mechanics and Materials*, 773–774, 725–728.
- Byranvand, M. M., Kharat, A. N., Fathollahi, L., & Beiranvand, Z. M. (2013). A Review on Synthesis of Nano-TiO<sub>2</sub> via Different Methods. *Journal of Nanostructures*, 3, 1–9.
- Byrappa, K., & Yoshimura, M. (2008). Hydrothermal processing of materials: past, present and future. *Journal Material Science*, 43, 2085–2103.
- Dhandayuthapani, T., Sivakumar, R., & Ilangoan, R. (2016). Single Step Synthesis of Rutile TiO<sub>2</sub> Nanoflower Array Film by Chemical Bath Deposition Method. In M. Singh Shekhawat, S. Bhardwaj, & B. Suthar (Eds.), *International Conference on Condensed Matter and Applied Physics (ICC 2015)* (Vol. 1728, pp. 1–5). Bikaner, Rajasthan: AIP Publishing.
- Di Paola, A., Bellardita, M., & Palmisano, L. (2013). Brookite, the Least Known TiO<sub>2</sub> Photocatalyst. *Catalysts*, 3, 36–73.
- Hamed, A. N. K., Noor, K. S., Fazli, M. F. I., Luqman, N. M. M., Nayan, N., & Ahmad, M. K. (2016). Influence of Hydrochloric Acid Volume on the Growth of Titanium Dioxide (TiO<sub>2</sub>) Nanostructures by Hydrothermal Method. *Sains Malaysiana*, 45(11), 1669–1673.
- He, Z., Cai, Q., Fang, H., Situ, G., Qiu, J., Song, S., & Chen, J. (2013). Photocatalytic activity of TiO<sub>2</sub> containing anatase nanoparticles and rutile nanoflower structure consisting of nanorods. *Journal of Environmental Sciences (China)*, 25(12), 2460–2468.
- Houas, A., Lachheb, H., Ksibi, M., Elaloui, E., Guillard, C., & Herrmann, J. (2001). Photocatalytic degradation pathway of methylene blue in water. *Applied Catalysis B: Environmental*, 31, 145–157.
- Huang, J., Cao, Y., Liu, Z., Deng, Z., & Wang, W. (2012). Application of titanate nanoflowers for dye removal: A comparative study with titanate nanotubes and nanowires. *Chemical Engineering Journal*, 191, 38–44.
- Kaplan, R., Erjavec, B., Drazic, G., Grdadolnik, J., & Pintar, A. (2016). Simple synthesis of anatase/rutile/brookite TiO<sub>2</sub> nanocomposite with superior mineralization potential for photocatalytic degradation of water pollutants. *Applied Catalysis B: Environmental*, 181, 465–474.
- Karkare, M. M. (2014). Choice of precursor not affecting the size of anatase TiO<sub>2</sub> nanoparticles but affecting morphology under broader view. *International Nano Letters*, 4(111), 1–8.
- Khalid, N. S., Wanzaki, W. S., & Ahmad, M. K. (2015). Growth of Rutile Phased Titanium Dioxide (TiO<sub>2</sub>) Nanoflowers for HeLa Cells Treatment. In V. Toi & T. Lien Phuong (Eds.), *5th International Conference on Biomedical Engineering in Vietnam* (pp. 243–246). Switzerland: Springer, Cham.
- Li, M., Jiang, Y., Ding, R., Song, D., Yu, H., & Chen, Z. (2013). Hydrothermal Synthesis of Anatase TiO<sub>2</sub> Nanoflowers on a Nanobelt Framework for Photocatalytic Applications. *Journal of Electronic Materials*, 42(6), 1290–1296.
- Ma, J., Ren, W., Zhao, J., & Yang, H. (2016). Growth of TiO<sub>2</sub> nanoflowers photoanode for dye-sensitized solar cells. *Journal of Alloys and Compounds*, 9(134), 1–21.
- Mali, S. S., Betty, A. C., Bhosale, N. P., Devan, S. R., Ma, Y.-R., Kolekar, S. S., & Patil, S. P. (2012). Hydrothermal synthesis of rutile TiO<sub>2</sub> nanoflowers using Brønsted Acidic Ionic Liquid [BAIL]: Synthesis, characterization and growth mechanism. *CrystEngComm*, 14, 1920–1924.
- McNulty, G. S. (2008). Production of titanium dioxide. In *Naturally Occurring Radioactive Material (NORM V)* (pp. 169–187). Seville: International Atomic Energy Agency (IAEA).
- Miao, H., Hu, X., Fan, J., Li, C., Sun, Q., Hao, Y., Zhang, G., Bai, J., & Hou, X. (2015). Hydrothermal synthesis of TiO<sub>2</sub> nanostructure films and their photoelectrochemical properties. *Applied Surface Science*, 358, 418–424.
- Min, L., Wei-ming, L., Lei, Z., & Chun-lan, Z. (2010). Fabrication and photocatalytic properties of flower-like TiO<sub>2</sub> nanostructures. *Transactions of Nonferrous Metals Society of China*, 20(12), 2299–2302.
- Pal, M., Serrano, J. G., Santiago, P., & Pal, U. (2007). Size-controlled synthesis of spherical TiO<sub>2</sub> nanoparticles: Morphology, crystallization, and phase transition. *Journal of Physical Chemistry C*, 111(1), 96–102.
- Paulauskas, I. E., Modeshia, D. R., Ali, T. T., El-Mossalmy, E. H., Obaid, A. Y., Basahel, S. N., Al-Gamdi, A. A., & Sartain, F. K. (2013). Photocatalytic Activity of Doped and Undoped Titanium Dioxide Nanoparticles Synthesised by Flame Spray Pyrolysis. *Platinum Metals Review*, 57(1), 32–43.
- Phan, T. N., Pham, H., Cuong, T. V., Kim, E. J., Kim, S., & Å. E. W. S. (2009). A simple hydrothermal preparation of TiO<sub>2</sub> nanomaterials using concentrated hydrochloric acid. *Journal of Crystal Growth*, 312(1), 79–85.
- Prabhu, S., & Poulose, E. K. (2012). Silver nanoparticles: mechanism of antimicrobial action, synthesis, medical applications, and toxicity effects. *International Nano Letters*, 2(1), 32.
- Qu, X., Alvarez, P. J. J., & Li, Q. (2013). Applications of nanotechnology in water and wastewater treatment. *Water Research*, 47, 3931–3946.
- Reyes-Coronado, D., Rodriguez-Gattorno, G., Espinosa-Pesqueira, M. E., Cab, C., de Coss, R., & Oskam, G. (2008). Phase-pure TiO<sub>2</sub> nanoparticles: anatase, brookite and rutile. *Nanotechnology*, 19(14), 1–10.
- Roy, H. G. (2013). Optical Properties and Photocatalytic Activities of Titania Nanoflowers Synthesized by Microwave Irradiation. *International Journal of Innovative Research in Science, Engineering and Technology*, 2(6), 2175–2181.
- Safarpour, M., Khataee, A., & Vatanpour, V. (2015). Thin film nanocomposite reverse osmosis membrane modified by reduced graphene oxide/TiO<sub>2</sub> with improved desalination performance. *Journal of Membrane Science*, 489, 43–54.
- Sekino, T. (2010). Synthesis and applications of titanium oxide nanotubes. In T. Kijima (Ed.), *Inorganic and Metallic Nanotubular Materials: Recent Technologies and Applications* (1st ed., Vol. 117, pp. 17–32). Tokyo: Springer-Verlag Berlin Heidelberg.
- Seok, S. II, Vithal, M., & Chang, J. A. (2010). Colloidal TiO<sub>2</sub> nanocrystals prepared from peroxotitanium complex solutions: Phase evolution from different precursors. *Journal of Colloid And Interface Science*, 346(1), 66–71.
- Shinde, P. S., Betty, C. A., Bhosale, P. N., Lee, W. J., & Patil, P. S. (2011). Applied Surface Science Nanocoral architecture of TiO<sub>2</sub> by hydrothermal process: Synthesis and characterization. *Applied Surface Science*, 257(23), 9737–9746.
- Song, H., Chen, T., Sun, Y., Zhang, X.-Q., & Jia, X. (2014). Controlled synthesis of porous flower-like TiO<sub>2</sub> nanostructure with enhanced photocatalytic activity. *Ceramics International*, 40(7), 11015–11022.
- Song, Z., Zhou, H., Tao, P., Wang, B., Mei, J., Wang, H., Wen, S., Song, Z., & Fang, G. (2016). The Synthesis of TiO<sub>2</sub> Nanoflowers and their Application in Electron Field Emission and Self-powered Ultraviolet Photodetector. *Materials Letters*, 180, 179–183.
- Sun, J., Wen, W., & Wu, J. (2013). Low-Temperature Transformation of Titania Thin Films from Amorphous Nanowires to Crystallized Nanoflowers for Heterogeneous Photocatalysis. *Journal of American Ceramic Society*, 7(96), 2109–2116.
- Tang, G., Liu, S., Tang, H., & Zhang, D. (2013). Template-assisted hydrothermal synthesis and photocatalytic activity of novel TiO<sub>2</sub> hollow nanostructures. *Ceramics International*, 39(5), 4969–4974.
- Theivasanthi, T., & Alagar, M. (2013). Titanium dioxide (TiO<sub>2</sub>) Nanoparticles

- XRD Analyses: An Insight. *Arxiv Materials Science*, 1091, 1307–1316.
- Wang, Y., He, Y., Lai, Q., & Fan, M. (2014). Review of the progress in preparing nano TiO<sub>2</sub>: An important environmental engineering material. *Journal of Environmental Chemical Engineering*, 26(11), 2139–2177.
- Wu, J.-M., Huang, B., Wang, M., & Osaka, A. (2006). Titania Nanoflowers with High Photocatalytic Activity. *Journal American Ceramic Society*, 2663(21379), 2660–2663.
- Xu, F., Wu, Y., Zhang, X., Gao, Z., & Jiang, K. (2012). Controllable synthesis of rutile TiO<sub>2</sub> nanorod array, nanoflowers and microspheres directly on fluorine-doped tin oxide for dye-sensitised solar cells. *Micro & Nano Letters*, 7, 826–830.
- Xu, H., Li, G., Zhu, G., Zhu, K., & Jin, S. (2015). Enhanced photocatalytic degradation of rutile/anatase TiO<sub>2</sub> heterojunction nanoflowers. *Catalysis Communications*, 62, 52–56.
- Yang, S., & Gao, L. (2006). Fabrication and shape-evolution of nanostructured TiO<sub>2</sub> via a sol – solvothermal process based on benzene – water interfaces. *Materials Chemistry and Physics*, 99, 437–440.
- Yin, B., Wang, J., Xu, W., Long, D., Qiao, W., & Ling, L. (2013). Preparation of TiO<sub>2</sub>/mesoporous carbon composites and their photocatalytic performance for methyl orange degradation. *Carbon*, 56, 393–394.